



Filter Element: 12-32-50C

Technical Specification	
Description	Disposable Coalescing Filter Element
Materials of Construction	Borosilicate Glass Microfibres bonded with Kynar fluorocarbon (P.V.D.F) resin
Filtration Efficiency	Better than 99.99+% removal of 0.1 micron particles and aerosols
Air Flow Resistance	Less than 2.8KPa at 6m ³ /min in air at 25°C
Dimensions	I.D. - 12.5mm ± 0.25mm
	O.D. - 19.0mm ± 1.5mm
Strength (dry)	Length - 32.5mm ± 0.25mm
	Burst minimum - 5.0 Bar
Temperature Resistance	Collapse minimum - 2.0 Bar
	-50°C to +150°C maximum air
Chemical Resistance	Resistant to all mineral, vegetable
	And synthetic compressor lubricants
	Consult chemical resistance chart for
	Other gases and liquids



For further specific information please contact our Technical Department
This is a guide only

Headline Filters Limited Mill Hall Business Estate Aylesford Kent, ME20 7JZ www.headlinefilters.com info@headlinefilters.com	Filter Element: 12-32-50C	
	Material: Borosilicate Glass Microfibres bonded with Kynar fluorocarbon (P.V.D.F) resin	
DO NOT SCALE DRAWING IF IN DOUBT ASK		

THE COPYRIGHT OF THIS DRAWING IS
RESERVED BY HEADLINE FILTERS. IT
IS ISSUED ON CONDITION THAT IT IS
NOT COPIED, REPRODUCED OR
DISCLOSED TO A THIRD PARTY
EITHER WHOLLY, OR IN PART
WITHOUT CONSENT IN WRITING.